

## SUITABLE FOR ALL TYPES OF WOOD\*

\*Please allow cedar to age a minimum of 6 months before applying the oil.

Considering the ecological composition of our products, we recommend cleaning only using GLOUROS 1806. Any other cleaning or surface preparation product could hinder proper oil adhesion.

## SURFACE PREPARATION

The wood must be completely dry, dust free and nonsealed. We recommend refreshing the oxidized surface by sanding the wood with a 100 grit sanding paper. Apply at temperature of at least 10°C and make sure the temperature remains over 10°C for at least 8 hours after application.

## OIL APPLICATION

### 1<sup>st</sup> COAT

Stir well with a stick to evenly mix the colour pigments in the oil. Apply the stain on a small surface to confirm your colour choice. Apply the coat with a brush, spray gun, applicator pad or with a roller just enough to saturate the wood. Let the surface absorb the oil for about 5 minutes then spread out the surface with a brush and make sure the surface is uniform. Wait about 18 hours before applying the second coat.

### 2<sup>nd</sup> COAT

Apply the second coat more sparingly and spread out on the surface with a brush after 5 to 10 minutes. On sidings, windows frame or other surfaces, a third coat is recommended; use the same process as the second coat.

## CLEANING

We recommend washing the terraces every year with GLOUROS 1806.

### NOTE - CARE

Wash with GLOUROS 1806 and refresh the surface with a new coat of ALIS 579 as soon as the surface shows signs of wear or become extremely tarnished. (Usually every year on terrace, and 3 to 5 years on siding)

## IMPORTANT BEFORE STARTING APPLICATION

As our products are coloured using natural pigments, there may be colour variations between batches. Therefore, it's essential to make a test on a small surface before completing your project. Make sure the result matches your expectation before proceeding.

Moreover, the wood preparation and it's age may also influence colour absorption, and final results may vary accordingly. We are not responsible for the final colour obtained in the event no test were performed or if multiple coloured oils were blended.

**THE RESPONSIBILITY OF THE  
DISTRIBUTOR AND THE MANUFACTURER  
IS LIMITED TO THE VALUE OF THE  
PRODUCT.**

**PLEASE NOTE THAT COLORLESS  
579-002 DOES NOT CONTAIN UV  
PROTECTION**

## WARNINGS

TO AVOID SPONTANEOUS COMBUSTION RISKS, RAGS, POLISHING DISCS AND OIL IMPREGNATED APPLICATOR PADS MUST BE PLACED IN A METALLIC SEALED CONTAINER OR SUBMERGED IN WATER BEFORE THEIR DISPOSAL.

version 1

LIVOS CANADA  
T. 1 877 909-3123 - F. 418 365-7915  
20, route Goulet, Proulxville (Québec) G0X 2B0

LIVOS.CA

## Technical Data Sheet

# ALIS Decking Oil No. 579

<b>Application range</b>	For exterior use (exception: colorless), as a treatment for terraces, facades, doors, play equipment, garden furniture and windows made of untreated solid wood. Suitable for beehives (outer part).			
<b>Technical qualities</b>	Impregnated, water repellent, and UV resistant surface. Complies with the German Industrial Norm DIN 53 160, fast to perspiration and saliva. Free of organic-chemical compounds according to DIN EN 71 part 9. Free of preservatives and biocides.			
<b>Full declaration</b>	Depending on the color possibly different ingredients: Isoaliphates, linseed oil - stand oil - natural resin ester, wood oil, mineral pigments, titanium dioxide (only in color 069, 212, 748, 794, 922, 1124, 1125, 1126), linseed oil, silicic acid, dehydrated amino sugar, castor oil - stand oil, linseed oil - wood oil - stand oil, linseed oil - stand oil, soy lecithin, chalk, kaolin, and drying agents free of lead (Ca, Mn, Zr).			
<b>Colors</b>	022 Boxtree	048 Chestnut	052 Brazil	064 Dark walnut
	068 Light teak	069 Tobacco	072 Oak	101 Black
	212 Light grey	439 Bongossi	554 Oregon Pine	593 Larch
	748 Slate-grey	794 Agate grey	922 Silver-grey	1122 Espresso
	1124 Grey willow	1125 Sesame	1126 Sienna	
	<b>002 Colorless (without UV protection)</b>			
	The color chestnut corresponds to the color tone of many exotic hardwoods.			
	Depending on the type of wood and the surface roughness, the color impression can vary considerably. The rougher the wood, the darker the color.			
<b>Application method</b>	2 – 3 applications with a brush, roller or spray gun (10% diluted). See reverse for further information.			
<b>Coverage</b>	Must be determined by doing a test application.			
	<u>For profiled (fluted) wood:</u>			
	First coat:	1 liter (1.06 quart) is sufficient for approx. 7 m <sup>2</sup> (75 ft <sup>2</sup> ), i.e., 140ml/m <sup>2</sup> .		
	Second coat:	1 liter (1.06 quart) is sufficient for approx. 35 m <sup>2</sup> (377 ft <sup>2</sup> ), i.e., 30ml/m <sup>2</sup> .		
	<u>For planed wood:</u>			
	First coat:	1 liter (1.06 quart) is sufficient for approx. 20-25 m <sup>2</sup> (215-269 ft <sup>2</sup> ), i.e., 40-50ml/m <sup>2</sup> .		
	Second coat:	1 liter (1.06 quart) is sufficient for approx. 40-50 m <sup>2</sup> (430-538 ft <sup>2</sup> ), i.e., 20-25ml/m <sup>2</sup> .		
	<u>For sanded wood (120-150 grain):</u>			
	First coat:	1 liter (1.06 quart) is sufficient for approx. 35-50 m <sup>2</sup> (377-538 ft <sup>2</sup> ), i.e., 20-30ml/m <sup>2</sup> .		
	Second coat:	1 liter (1.06 quart) is sufficient for approx. 55-70 m <sup>2</sup> (529-753 ft <sup>2</sup> ), i.e., 14-18ml/m <sup>2</sup> .		
<b>Drying time</b>	At 23 °C (73 °F) and 50% relative humidity: approximately 5 to 8 hours. The 2 <sup>nd</sup> and 3 <sup>rd</sup> coat can be applied after approximately 18 hours. At higher temperatures, please consider shorter drying times, and by lower temperatures, longer drying times.			
<b>Cleaning</b>	Clean equipment immediately after use with SVALOS Thinner No. 222 or LEVO Brush Cleaner No. 997.			
<b>Specific gravity</b>	Approximately 0.87 g/ml.			
<b>Safety advice</b>	Ensure good ventilation during and after application. Always be sure to store and then dispose of cleaning cloths, polishing pads, sponges, etc. that are still wet or even slightly moist with ALIS Decking oil N° 579 in an airtight metal container or in water, as there is a danger of spontaneous combustion caused by the plant oil content. The liquid and processed product is not self-ignitable.			
	P102	Keep out of reach of children.		
	P301+P310	IF SWALLOWED: Rinse mouth. Do NOT induce vomiting. Immediately call a doctor.		
	EUH211	Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist.		
<b>Disposal</b>	According to locally regulated laws.			
<b>Container sizes</b>	0.05 l; 0.375 l; 0.75 l; 2.5 l; 5.0 l; 10.0 l; 30.0 l.			
<b>Storage</b>	Cool and dry. Shelf life: unopened at least 4 years. Opened products react with oxygen, over time skin formation and rancid smell can occur. Residues should be transferred into smaller containers.			

How to use

## ALIS Decking Oil No. 579

<b>Preparation</b>	The surface must be absorbent, solid, dry, and free of dust. If necessary, remove moss, algae, fungus, etc. with GLOUROS-Cleaner No. 1806 completely. Protect the dry terrace with a tarpaulin against dew in the evening before; otherwise wait until dry.
<b>Application</b>	Remove possible skin formed on surface and stir thoroughly. Test adhesiveness by doing a test application (beading effects e.g., point to incompatibilities or to high wood moisture) Apply with a brush or roller in the direction of the wood grain at temperatures above 10 °C (50 °F), low humidity and dry weather. The applications should be done within 4 weeks. Observe drying times between each coat! If using a spray gun, dilute ALIS with 10% SVALOS No. 222, 292 or 293.
Terraces, play equipment, garden furniture	Apply the 1 <sup>st</sup> coat generously until the wood is saturated. After 15 minutes spread and, if necessary, remove oil supernatants Apply the 2 <sup>nd</sup> and the 3 <sup>rd</sup> coat <b>very thinly</b> .
Windows, doors:	Pre-sand gradually in accordance with the grading of the sandpaper grain, and up to 180. Apply the 1 <sup>st</sup> coat generously until the wood is saturated by brush or with a short-hair roller in the direction of the wood grain. Spread excess oil with a brush after 10 – 20 minutes (depending on the temperature). Second and third application <b>very thin</b> . Observe the absorbency of the wood: If necessary, apply the second coat thickly too until the wood is saturated and spread excess oil with a brush after 5-10 minutes. (A layer formation should be reached after the second coat = a silky gloss is recognizable). Seams of new windows should be wiped immediately after the first application with a lint-free cotton cloth and not treated anymore. Silicone should be applied only after complete drying. Windows and doors should have the same layer thickness inside and outside with the same product to ensure an optimal moisture transport.
Facades:	Treat planed wood in such a way, that it is sated. Spread excess oil after approximately 5 – 20 minutes, depending on the outside temperature. Second and third application according to the instruction for windows.
Beehives:	Same treatment as facades.
<b>Cleaning</b>	Clean with GLOUROS Cleaner No. 1806 at least once a year.
<b>Care</b>	Do after care with ALIS Decking Oil No. 579 when weathering or an extreme loss of gloss becomes visible.
<b>Important tips</b>	Please treat strongly weathered exterior areas, only when the wood is completely dry. The moisture content of Bangkirai and teak decreases slowly. The adhesiveness can be impaired in case of already impregnated wood or due to soiling by oils, grease etc.  If the stain drips off or bubbles appear during application, an incompatibility exists through the pre-treatment or it has been sanded to smooth. Coarser sanding may possibly create remedy.

These directions are the result of long years of research and practical testing. They are backed by our most current expert information. New findings may invalidate this information. The latest version is available on our website at [www.livos.de](http://www.livos.de). This data sheet is meant to serve as information and instruction. No legal liability should be interpreted from it. In case of doubt, please contact the LIVOS customer service (see page 1).

June 2021